

XRR and XMCD investigation of 120 MeV Ag⁸⁺ ion irradiation in Fe/MgO/Fe multilayer

Jitendra Pal Singh¹, Sanjeev Gautam², Weol Cheol Lim¹, K. Asokan³, D. Kabiraj³, D. Kanjilal³ and Keun Hwa Chae¹

¹Advanced Analysis Center, Korea Institute of Science and Technology, Seoul-02792, S. Korea

²Dr. S S Bhatnagar, University Institute of Chemical Engineering & Technology(SSB UICET), Panjab University, Chandigarh-160014, India

³Inter University Accelerator Centre, Aruna Ali Asaf Marg, New Delhi-110067, India

For present investigation, Fe/MgO/Fe multilayers has been grown on Si-substrate by e-beam evaporation method in ultra high vacuum (2×10^{-8} Torr), details are discussed earlier [1]. Multilayer sequence from substrate is as follows: MgO(10)/Fe(20)/MgO(5)/Fe(10)/Au(5) (Values in parenthesis are thickness in nm). The multilayer stack has been irradiated by using 120 MeV Ag⁸⁺ at different fluencies ranging from 1×10^{11} to 1×10^{13} ions/cm² in ultra-high vacuum by using Pelletron Accelerator at IUAC, New Delhi. XRR analysis shows that thickness of various layers for pristine stack are 11, 12, 6, 7, 4 nm for MgO, Fe, MgO, Fe, and Au layers in the stack respectively. In the XRR analysis Fe-O_x layer of thickness 1.3 and 1.9 nm has also been considered at Fe/MgO and MgO/Fe interfaces. Further analysis carried out on irradiated stack shows change in interface roughness with fluence of irradiation and slight increase of Fe-oxidation at interface. It may be contemplated that confined energy in the stack by the heavy-ions increases the possibility of intermixing at interface, resulting the Fe-O_x to be thicker. Fe L-edge near edge fine structure (NEXAFS) measurements shows presence of Fe²⁺ and Fe³⁺ valence state with dominant feature corresponding to Fe³⁺ states in pristine as well as irradiated samples. It is well established that magnetic moment aligned along the direction of ion-trajectory during the irradiation experiment [2]. Since, SHIs incident perpendicular to the film surface during irradiation, hence the dominant changes are observed in the perpendicular hysteresis. This is in agreement with X-ray magnetic circular (XMCD) measurements where the in plane XMCD signal intensity reduces with fluence from 9.6% to 0% at room temperature. This envisages that few magnetic moments are aligned in the direction of ion trajectory reducing the strength of the in-plane XMCD signal at room temperature. Alignment of magnetic moment in irradiated material has also been discussed in our previous work [3]. The detailed investigation and correlation of magnetization with interface is under investigation.

Acknowledgements

Authors are thankful to Pelletron Group, Inter University Accelerator Centre (IUAC), New Delhi for their active support during irradiation experiment (BTR-49101).

References:

1. J. P. Singh, **S. Gautam**, Brajbhushan Singh, K. Asokan, D. Kabiraj, D. Kanjilal, M. Raju, S. Chaudhary, R. Kotnala and K. H. Chae. *r Adv. Mat. Lett.* 2014, **5(7)**, 372-377
2. F. Studer, C. Houpert, D. Groult, J. Yun Fan, A. Meftah, M. Toulemonde, *Nucl. Instr. Methds Phys. Res.* **B82** (1993) 91-97.
3. J. P. Singh, Gagan Dixit, H. Kumar, R.C. Srivastava, H.M. Agrawal, R. Kumar, J. Magn. *Magn. Mater.* **352** (2014) 36-44