

Analysis of stability diagram of perpendicular magnetic tunnel junctions

Witold Skowroński¹, Maciej Czapkiewicz¹, Sławomir Ziętek¹, Jakub Chęciński¹, Marek Frankowski¹, Piotr Rzeszut¹, Jerzy Wrona²

¹AGH University of Science and Technology, Department of Electronics, Magnetic Multilayers and Spin Electronics Group, Al. Mickiewicza 30, 30-059 Kraków, Poland

²Singulus Technologies, Kahl am Main, 63796, Germany

Magnetic tunnel junctions (MTJs) have become a basic building blocks of contemporary spintronics devices, such as spin transfer torque magnetic random access memory (STT-MRAM) cells, microwave generators and detectors [1]. Various properties of such devices can be improved by using ferromagnetic materials with perpendicular magnetic anisotropy [2].

We present a study on such perpendicular MTJs with a composite CoFeB/W/CoFeB free layer (FL) of different thickness and Co-Pt-superlattice-pinned CoFeB reference layer, deposited using Singulus Timaris sputtering system, which reveal up to 180 % of tunneling magnetoresistance (TMR) ratio and perpendicular anisotropy field of up to 450 kA/m. The effective magnetic damping (α) parameter was determined using vector network analyzer ferromagnetic resonance method and increased from 0.038 up to 0.087 with increasing FL thickness, which coincides with a decrease of effective magnetization from 450 to 15 kA/m, the latter value being close to an in-plane magnetization orientation.

Voltage vs. perpendicular magnetic field switching diagrams were measured in MTJs patterned into 130 nm diameter nanopillars with different thickness of the FL. An extension of model presented in Ref. [4] was proposed, taking into account not only STT but also voltage control of magnetic anisotropy (VCMA) and thermal effects. For the thinnest FL ($t_{FL} = 1.1$ nm), which manifest the smallest α and the highest effective magnetization, we obtained damping-like STT coefficient $\tau_{DL} = 4.5e-19$ Nm and VCMA of $\kappa = 46$ fJ/Vm. The VCMA coefficient increases, whereas τ_{DL} remains almost constant, for MTJs' FL thickness FL [5].

Acknowledgements

The project is supported by Polish National Center for Research and Development grant No. LIDER/467/L-6/14/NCBR/2015. Nanofabrication process was performed at Academic Center for Materials and Nanotechnology of AGH University.

[1] L. Stamps et al. J. Phys. D: Appl. Phys. 47, 333001 (2014)

[2] S. Ikeda et al. Nat Mater, 9, 721 (2010)

[3] H. T. Nembach et al. Phys. Rev. B 84, 054424 (2011)

[4] K. Bernert et al. Phys Rev. B 89, 134415 (2014)

[5] W. Skowroński et al. Sci. Rep. 7, 10172 (2017)