

**ZnAs<sub>2</sub>—MnAs system phase diagram creation.**

S. F. Marenkin<sup>1</sup>, I. V. Fedorchenko<sup>1,2</sup>, O. I. Rabinovich<sup>2</sup>, S. I. Didenko<sup>2</sup>,  
S. A. Legotin<sup>2</sup>, M.N. Orlova<sup>2</sup>

<sup>1</sup>Kurnakov Institute of General and Inorganic Chemistry RAS, Moscow, Russian Federation

<sup>2</sup>National University of Science and Technology, Leninskiy pr., 135 049, Moscow, Russian Federation

The ZnAs<sub>2</sub> — MnAs system was investigated by X – ray power diffraction, thermo differential and microstructure analyses. The system is an eutectic type. The eutectic coordinates are 73 mol % ZnAs<sub>2</sub>, 27 mol % MnAs and  $T_{\text{melt}} = 716\text{ }^{\circ}\text{C}$ . The MnAs solubility in ZnAs<sub>2</sub> was lower than ~1 mol %. Zinc diarsenide with manganese arsenide compound was ferromagnetic, with  $T_c \sim 318\text{ K}$ . Compound magnetization was increased with MnAs content rise.